## JP2002096105

| P | uh | ۱lia | S  | ti. | Λi | า - | Fit | le: |
|---|----|------|----|-----|----|-----|-----|-----|
|   | uL | иι   | Ja | u   | OΙ |     | ıιι | ıc  |

METHOD FOR MANUFACTURING HIGH-STRENGTH STEEL PIPE


Abstract:


Abstract of JP 2002096105

(A) PROBLEM TO BE SOLVED: To manufacture a high-strength steel pipe which restrains inner flaws from being caused and which is excellent in resistance to sulfide, stress and corrosion cracking. SOLUTION: Seemless pipes are manufactured by the direct hot rolling of billets made by continuously casting low-alloy steel containing C of 0.2-0.3 wt.%, Si of 0.1-0.3 wt.%, Mn of 0.1-0.3 wt.%, P of 0.15 wt.% or less, S of 0.002 wt.% or less, Cr of 0.5-1.5 wt.%, Mo of 0.2-1.0 wt.%, Nb of 0.01-0.05 wt.%, B of 0.0005-0.005 wt.%, O of 0.005 wt.% or less and H of 0.0005 wt.%, and the seemless pipes are then subjected to heat treatment such as quenching and tempering.

-----

Courtesy of http://v3.espacenet.com





## フロントページの続き

| (51)Int.C1.7 |       | 識別記号 | FI      |       | テーマコード(参考) |
|--------------|-------|------|---------|-------|------------|
| B 2 2 D      | 11/12 |      | B 2 2 D | 11/12 | A          |
| C 2 1 D      | 9/08  |      | C 2 1 D | 9/08  | E          |
| // C22C      | 38/00 | 301  | C 2 2 C | 38/00 | 301Z       |
|              | 38/32 |      |         | 38/32 |            |

(72)発明者 橋爪 修司 東京都千代田区丸の内一丁目1番2号 日 本鋼管株式会社内 F 夕一ム(参考) 4E002 AA04 AB06 BB08 BD02 CB03 CB10 4K042 AA06 BA01 BA07 CA02 CA03 CA06 CA08 CA09 CA12 CA13 CA14 DA01 DA02 DC02 DD02 DE02